



Polymer-Modified, Portland Cement Based Plaster Finish For Interior Surfaces



Coverage

Approximately 120 to 130 sq-ft per 50lb bag

Packaging

Multi-layered, moisture resistant, 50 lb. bags.

Storage

1. Protect bags from weather and other damage
2. Store bags in a cool, dry location
3. Store out of direct sunlight
4. Store away from direct contact with the ground and/or concrete

Shelf Life

1 Year

Color

Off-White

Custom colors are also available.



SCAN FOR
FULL LIST
OF SPEC SHEETS

Product Description

Superior Interior Finish is a mechanically-blended compound of portland cement, hydrated lime, inert aggregates, and specific additives, designed to achieve a steel trowel or floated finish over properly prepared interior surfaces. It requires the addition of only clean water for mixing. Custom colors are available through the Superior Stucco Color Pack System.

Basic Uses

Provides a hardy, enduring finish over properly prepared drywall and painted surfaces. Superior Interior Finish will provide excellent bond to any properly prepared interior surface. If you prefer to color Superior Interior Finish, it will achieve its own variance of color. It may be used on interior surfaces to provide a highly condensed, smooth surface. May use sealer or to be painted.

Area of Use

1. Bedrooms
2. Bathrooms
3. Kitchens and Outdoor Kitchen Areas
4. Offices

Features & Benefits

- Color integrated
- Lasting durability, protects as it decorates.
- Mixes easily with potable water.
- Low maintenance, economical.
- Adds aesthetic value to any building.
- Mold resistant

Optional Product Upgrades/Enhancements

Product	Benefit
Admix 2000, Ultra-Tite 60, Acrylic Bonder	Liquid admixtures that reduce cracking and increase tensile, bond, and flexural strengths.

INTERIOR FINISH SHEET

Surface Preparation

All receiving surfaces must be structurally sound, clean, free of dust, dirt, silicones, paint products, efflorescence or any other contaminant which could impair the natural bond. Surface defects, such as cracks, holes or voids should be repaired prior to application. Basecoat should be plum, level, and square to prevent uneven thickness of Superior Interior Finish. All previously painted surfaces must be dry and if glossy, should be etched.

Mixing

Superior Interior Finish should be mechanically mixed for approximately 10 minutes to a thin consistency until smooth and free of lumps to provide maximum workability. Use a long margin trowel to scrape edges of mix bucket to remove any dry powder and prevent clumps.

For Hand Application: 3 to 5 qts. of clean water per 50 lb. bag will be necessary. Add approximately 1/2 of the required water to the mixer. With the blades running, carefully add the Superior Interior Finish. Allow ample time for initial mixing, add remaining mix water, and complete mixing to produce a smooth, workable consistency. Disengage mixing and let the material take on its' initial "set" (3 to 5 minutes), then adjust water to desired consistency and only mix long enough to achieve desired material.

For Machine or Spray Application: Additional mixing water may be necessary.

NOTE: For maximum strength and increased moisture resistance, add Superior Acrylic Bonder to the mix water using a 3:1 ratio (3 parts water/1 part Acrylic Bonder).

Application

If surface is painted, apply Superior Stucco Multi-Bond. Superior Interior Finish should be applied to an approximate thickness of 1/8 inch (3mm). Pre-treat all wallboard joints by embedding mesh joint tape with Superior Interior Finish. Trowel apply an even coat to the substrate with enough pressure to ensure tight contact. Trowel or float to desired texture. Prior to drying out, you may water-trowel the surfaced to the desired or approved finish level, using as little water possible. Avoid unnecessary "build-ups" which cause shrinkage or check-cracking. A properly prepared basecoat will prevent leveling with the Superior Interior Finish.

NOTE: If painting over Interior Finish, please assure the alkali level is neutral, may cause efflorescence.

Limitations

DO NOT apply product when the ambient and surface temperature is below 40°F (4°C). Material that is allowed to freeze may suffer irreparable damage. Protect all work from inclement weather with an approved protective system until fully dry. It is the sole responsibility of the applicator to determine when this product is fully dry.

DO NOT apply Superior Stucco Interior Finish if there are contaminants on the receiving surface. Contaminates may include, but are not limited to, dust, debris, efflorescence, and or oils.

DO NOT add any more water than is prescribed when diluting the product.

DO NOT add any other materials to the mixture of the product without written consent of Superior Stucco

DO NOT deviate in the mixing or application procedures contained in this or related Product Information Sheet(s).

DO NOT use a Jiffler type mixer that exceeds 500RPM

NOTE: Failure to follow manufacturer's written specifications could result in the following, but not limited to spalling, cracking, peeling, chipping, delamination, discoloration, wash off, and overall system failure.

Due to job conditions beyond the control of Superior Stucco we make no warranty as to the acceptance of the final color. The actual integrally colored finish should be applied on a sample section of the project and verified for color accuracy prior to the actual application process.

Cleaning

Cleaning may be accomplished with water immediately after use.

Safety

Avoid contact with eyes or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush immediately with running water for at least 15 minutes. Consult a physician immediately. Do not take internally. Be sure to provide adequate ventilation in enclosed areas. Use of an approved respirator is recommended.

KEEP OUT OF REACH OF CHILDREN

www.StuccoSupplyCo.com

Disclaimer
Stucco Supply (Manufacturer) MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT(S) SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that the buyer's sole and exclusive remedy for any claimed defective product against Manufacturer shall be the replacement of products actually proven to be defective. Handling and use of the products

are beyond the control of Manufacturer; therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the product. Before applying the product, the user shall determine the suitability of the product for his/her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.

Claims
Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for the alleged defect. For any claim that is not valid Claimant agrees to pay Stucco Supply's reasonable charges, including travel and labor associated with investigation of such claim.

Technical Assistance
Technical assistance and information is available by calling (408) 292-0454

Warranty
The following is made in lieu of all expressed and implied rights, warranties and conditions, statutory or otherwise. The manufacturer's only obligation shall be to replace such quantity of products proven to be defective within one year following the date of manufacture, provided that the alleged defective product is returned prepaid to the manufacturer's plant and is accompanied with proof of purchase and batch number.