

# ***SUPERIOR STUCCO ADMIX 2000***

## **ACRYLIC POLYMER MODIFIER USED TO IMPROVE TENSILE STRENGTH IN CEMENT PRODUCTS**

### **DESCRIPTION:**

**SUPERIOR STUCCO ADMIX 2000** is a medium, viscous, low odor, acrylic polymer modified matrix used to fortify cement mortar mixes. **SUPERIOR STUCCO ADMIX 2000** increases mortar strength, water resistance, superior adhesion and UV protections, as well as offering superior versatility in many cement based mortar mixes. **SUPERIOR STUCCO ADMIX 2000** works well with One-Coat applications, exterior Stucco, Terrazzo, patching and concrete resurfacing; delivering durability, strength and decreases surface degradation, especially on thin applications like Stucco.

### **APPLICATIONS:**

Take care that all surfaces are clean and suitable for application. **HOT SURFACES SHOULD BE COOLED DOWN BY MISTING WATER ON SUBSTRATE PRIOR TO APPLICATION**, Saturated, Surface, Dry (SSD) procedure is recommended.

**Stucco Finish, Terrazzo and Mortar:** Mix One (1) part **SUPERIOR STUCCO ADMIX 2000** to Three (3) parts water (1:3). This will improve adhesion and reduce cracking. Use straight with concrete compounds for deep patching base.

**One-Coat Stucco:** Mix One (1) part **SUPERIOR STUCCO ADMIX 2000** to One (1) part water (1:1), then add to sand/cement mixture and mix normally.

### **COVERAGE:**

The coverage of the **SUPERIOR STUCCO ADMIX 2000** will vary due to job conditions, method of application, and weather conditions. Typically (1) Gallon of most of the **SUPERIOR STUCCO ADMIX 2000** will cover approximately 200-300 sq. feet (5 Gallons: 1,000-1,500 sq. ft) Yields will vary depending on dilution rate and porosity of substrate.

### **STORAGE:**

The **SUPERIOR STUCCO ADMIX 2000** should be stored in a cool, dry place out of direct sunlight. Keep above 40 degrees F and below 110 degrees F.

### **LIMITATIONS:**

Do not apply **SUPERIOR STUCCO ADMIX 2000** when the temperature is below 40 degrees F or above 100 degrees F. This range of temperature must be kept for 48 hours to ensure proper curing. Keep away from hydrostatic pressure (Moisture/water) after applying **SUPERIOR STUCCO ADMIX 2000**. Do not apply until surface is free of all contaminants. Please refer to the individual **SUPERIOR STUCCO product** for detailed information.

### **CLEAN UP:**

Clean up with water immediately. **DO NOT ALLOW TO DRY BEFORE CLEAN UP.**

### **GUARANTEE**

The above statement, recommendation, suggestions and technical data are based on the best knowledge to **Stucco Supply** and is given as information only, without any responsibility for their use. **Stucco Supply** makes no warranties or guarantees to this product, either expressed or implied with respect to merchantability or fitness for particular use of said product. Handling and use of product are out of the control of **Stucco Supply**, so no warranty is given.

**SAN JOSE STUCCO SUPPLY & DRYWALL - FROM START → TO FINISH**

1601 LITTLE ORCHARD STREET, STE. E SAN JOSE, CA 95110  
WWW.STUCCOSUPPLYCO.COM